



**INVICTUS**<sup>®</sup>

HEAVENLY COMFORT · INVINCIBLE FLOORING

## RECOMMENDED GLUES INVICTUS LOOSELAY

BRAND	ADHESIVE	SPECIFICATIONS	METHOD	CONSUMPTION /m <sup>2</sup>
EUROCOL	Eurocol 542 Eurofix Tack Plus (EC1)	30-60 min drying time (tackifier needs to be dry!)	low absorbent subfloor:	10kg: 200-100m <sup>2</sup> ; 50-100g/m <sup>2</sup>
			foam roller or brush	
			high absorbent subfloor:	10kg: 100-67m <sup>2</sup> ; 100-150g/m <sup>2</sup>
			foam roller or brush	
UZIN	UZIN U 1000	tackifier (tackifier needs to be dry!)	low absorbent subfloor:	10kg: 166-125m <sup>2</sup> ; 60-80g/m <sup>2</sup>
			foam roller	
			high absorbent subfloor:	10kg: 100-77m <sup>2</sup> ; 100-130g/m <sup>2</sup>
			microfiber roller	
UZIN	SIGAN 1	planks ≤130cm, on mineral subfloors, in combination with Planus primer	double-sided adhesive film	roll 75cm x 25m
UZIN	SIGAN ELEMENTS PLUS	high size stability, on mineral subfloors, epoxy dampscreens, chip boards, OSB, alu and steel, in combination with Planus primer	double-sided adhesive film	roll 75cm x 25m